

# Technical data sheet

## SC VIS HV P



### Description

SC VIS HV P is a formulation of cellulosic ethers proposed as an easily dispersible powder. SC VIS HV P is an efficient viscosifier and fluid loss reducer.

### Applications

SC VIS HV P is the product of choice for:

- D-wall construction, bored pile
- Slurry shield and EPBS tunneling
- Pipe jacking and horizontal directional drilling (HDD)
- All types of drainage works
- Water well drilling, soil sampling

### Benefits

- Cost effective as small amount are required
- Easy to use product
- Enhance viscosity and reduce filtrate loss of BENTONIL based mud
- Improve stability of BENTONIL mud in contaminated ground conditions e.g. salts, gypsum...
- SC VIS HV P based drilling fluids are fully compatible with conventional separation equipment
- Biodegradable
- Friendly to the environment

### Physical properties

Appearance	Free flowing powder
Apparent density:	0.6 – 0.7 g/cm <sup>3</sup>
pH of 0.2% solution :	7 – 8

CLARIANT (SINGAPORE) PTE. LTD.  
BU FUNCTIONAL MINERALS  
BL ADSORBENTS  
BUSINESS GROUP CIVIL ENGINEERING

1 International Business Park,  
#07-01 The Synergy,  
Singapore 609917  
[www.clariant.com](http://www.clariant.com)

COPYRIGHT ©  
CLARIANT INTERNATIONAL LTD 2012

EDITION  
April 2014

## Guidelines for use

### ▪ **Water based mud systems**

Depending on the application and soil conditions, the dosage range is between 0.5 to 3 kg/ m<sup>3</sup> of water. Recommended mixing time on low speed is 5-10 minutes.

### ▪ **Bentonite based mud systems**

Depending on the technique and soil conditions, the dosage range between 0.2 to 2 kg/ m<sup>3</sup> of bentonite suspension. SC VIS HV P should be added in a pre-hydrated bentonite suspension. Recommended mixing time on low speed is 5-10 minutes.

## Packaging

In 25 kg paper bags

## Storage

Keep the product in its original closed packaging above 0°C and no longer than 12 months.

## Related Documents

MSDS & application sheets available on demand. Contact your CLARIANT technical representative for any further information or references.

---

This information corresponds to the present state of our knowledge and is intended as a general description of our products and their possible applications. Clariant makes no warranties, express or implied, as to the information's accuracy, adequacy, sufficiency or freedom from defect and assumes no liability in connection with any use of this information. Any user of this product is responsible for determining the suitability of Clariant's products for its particular application.\* Nothing included in this information waives any of Clariant's General Terms and Conditions of Sale, which control unless it agrees otherwise in writing. Any existing intellectual/industrial property rights must be observed. Due to possible changes in our products and applicable national and international regulations and laws, the status of our products could change. Material Safety Data Sheets providing safety precautions, that should be observed when handling or storing Clariant products, are available upon request and are provided in compliance with applicable law. You should obtain and review the applicable Material Safety Data Sheet information before handling any of these products. For additional information, please contact Clariant.

® Trademark registered in many countries and owned by Clariant  
© 2012 Clariant International Ltd, Rothausstrasse 61, 4132 Muttenz, Switzerland

